

SIGMAWELD 210
(DIMETCOTE 210 SP)

4 pages

December 2009
Revision of October 2009

DESCRIPTION

two component moisture curing, zinc (ethyl) silicate prefabrication primer

PRINCIPAL CHARACTERISTICS

- suitable for automatic application on shot blasted steel plates
- fast drying properties
- good cutting and excellent welding properties, including MIG/MAG welding in various positions (either automatic or manual welding)
- provides corrosion protection up to 9 months
- can be used as a first coat in various paint systems
- suitable for sea water immersion in combination with controlled cathodic protection systems
- excellent thermal stability minimizes heat damage during hot work procedures
- no adherence of weldspatter at surrounding primed surface
- approved by Lloyd's Register of Shipping for use as prefabrication primer

COLOURS AND GLOSS

grey, reddish grey - flat

BASIC DATA AT 20°C

(1 g/cm³ = 8.25 lb/US gal; 1 m²/l = 40.7 ft²/US gal)
(data for mixed product)

Mass density

2.1 g/cm³

Volume solids

38 ± 2%

VOC (supplied)

max. 299 g/kg (Directive 1999/13/EC, SED)
max. 607 g/l (approx. 5.1 lb/gal)

Recommended dry film thickness

15 - 20 µm

Theoretical spreading rate

19 m²/l for 20 µm

Touch dry after

2 - 4 min. at substrate temperature of 20°C

1 -2 min. at substrate temperature of 40°C

Overcoating interval

min. 16 hours

max. 9 months

longer overcoating intervals can be permitted when primer is still in sound condition

(data for components)

Shelf life (cool and dry place)

binder: at least 6 months

paste: at least 12 months

**RECOMMENDED
SUBSTRATE CONDITIONS
AND TEMPERATURES**

- steel; shot blast cleaned to ISO-Sa2½, blasting profile 30 - 75 µm
- substrate temperature may be up to max. 35°C
- for automatic application a substrate temperature of 30°C is recommended
- substrate temperature should be at least 3°C above dew point
- relative humidity during curing should be above 50% and below 85%
- dust quantity rating "1" for dust size class "3", "4" or "5", lower dust size classes to be removed if visible on the surface to be coated without magnification (ISO 8502-3:1992)

SIGMAWELD 210
(DIMETCOTE 210 SP)

December 2009

SECONDARY SURFACE PREPARATION

- during storage and construction, contamination of the prefabrication primer should be limited
- after fabrication, surface defects should be treated according to the scheme below
- where two possible surface treatments are indicated, the choice of treatment is dependent on the location and on the system to be applied (see system sheets)
- the preferred pretreatment for optimal results is shown; other possibilities are indicated in brackets

areas	immersed conditions	atmospheric conditions
contamination	to be removed or ISO 8501-3 grade P2	to be removed
weldseams	ISO-Sa2½ (SPSS-Pt3) or ISO 8501-3 grade P2	SPSS-Pt2
burned	ISO-Sa2½ (SPSS-Pt3) or ISO 8501-3 grade P2	SPSS-Ss (SPSS-Pt2)
damaged corroded	ISO-Sa2½ (SPSS-Pt3) or ISO 8501-3 grade P2	SPSS-Ss (SPSS-Pt2)
white rust	SPSS-ID Pt2 (SCAP *) or ISO 8501-3 grade P2	SPSS-ID Pt1 (SCAP *)

* cleaning by silicon carbide impregnated abrasive pad

Dust quantity rating "1" for dust size class "3", "4" or "5", lower dust size classes to be removed if visible on the surface to be coated without magnification (ISO 8502-3).

Note that the back of welded plate may show discoloration (especially on plate where fillets have been welded on), this is not to be confused with burned areas and does not require special treatment.

Burned through areas may be present (this happens especially when welding thin steel) and these should then be treated as per 'burned areas' above.

INSTRUCTIONS FOR USE

mixing ratio by volume: binder to paste 50 : 50

- the temperature of the mixture of binder and paste should preferably be above 15°C
- stir the paste thoroughly before adding the binder
- add gradually one third of the binder to the pigment paste
- stir thoroughly till homogeneous
- add remaining binder and continue stirring until the mixture is homogeneous
- strain mixture through a 30 - 60 mesh screen
- mixed paint is ready for use
- some addition of thinner (Thinner 40-25) might be necessary depending on routing, line speed and steel temperature
- agitate continuously during application

Pot life

8 hours at 20°C

SIGMAWELD 210
(DIMETCOTE 210 SP)

December 2009

AIRLESS SPRAY

Recommended thinner Thinner 40-25
 Volume of thinner 0 - 35%, depending on required thickness and application conditions
 Nozzle orifice approx. 0.49 - 0.64 mm (= 0.019 - 0.025 in)
 Nozzle pressure 8 - 12 MPa (= approx. 80 - 120 bar; 1140 - 1700 p.s.i.)

AIR SPRAY

Recommended thinner Thinner 40-25
 Volume of thinner 0 - 35%, depending on required thickness and application conditions
 Nozzle orifice 1 - 1.5 mm
 Nozzle pressure 0.3 MPa (= approx. 3 bar; 43 p.s.i.)

CLEANING SOLVENT

Thinner 90-58

SAFETY PRECAUTIONS

for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets

this is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes

Worldwide availability

Whilst it is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

Explanation to product data sheets	see information sheet 1411
Safety indications	see information sheet 1430
Safety in confined spaces and health safety	
Explosion hazard - toxic hazard	see information sheet 1431
Cleaning of steel and removal of rust	see information sheet 1490
Relative humidity - substrate temperature - air temperature	see information sheet 1650

SIGMAWELD 210

(DIMETCOTE 210 SP)

December 2009

LIMITATION OF LIABILITY

The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the Sigma Coatings products made by PPG Protective & Marine Coatings, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. The products and information are designed for users having the requisite knowledge and industrial skills and it is the end-user's responsibility to determine the suitability of the product for its intended use.

PPG Protective & Marine Coatings has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. PPG Protective & Marine Coatings does therefore not accept any liability arising from loss, injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The data contained herein are liable to modification as a result of practical experience and continuous product development.

This data sheet replaces and annuls all previous issues and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product.

The English text of this document shall prevail over any translation thereof.

PDS

7159